

## 使用说明

### 1. 表面处理

仅敷涂于清洁、坚固、干燥和粗糙的表面；

- a) 擦除多余的泄漏材料；如果泄漏材料是水，则可使用干抹布擦除；并使用浸泡了贝尔佐纳(Belzona®)9111（清洗剂/脱脂剂）或其它无残留物的有效洗涤剂，例如甲基乙基酮(MEK)处理其它的污染物；
- b) 使用喷砂、深擦或打磨将使表面粗糙；
- c) 仅用于已稳定的裂缝；使用旋转锉将所有裂缝加工成V形；
- d) 最后再次除脂；并使用干净的抹布防止污染扩散。

将贝尔佐纳(Belzona®)材料刷涂到贝尔佐纳(Belzona®)9341（增强带）上；使用绷带覆盖需要修复的区域，并让已敷涂涂层的一面接触基材；

用力向下按压将所有裂缝填满，将缝隙内的空气排尽，确保材料与基材表面充分接触；

关于管道，将贝尔佐纳(Belzona®)9341紧紧地缠绕管道数圈，直到贝尔佐纳(Belzona®)材料透出贝尔佐纳(Belzona®)9341外；

### 2. 混合及配比

切下所需材料的份量并带上手套，用手指揉成均匀的灰色；将材料储存在20-25°C(68-77°F)之间有助于混合；

#### 操作时限

从混合开始，贝尔佐纳(Belzona®)9611应在4分钟内使用完毕。

### 3. 使用贝尔佐纳(BELZONA®)9611

使用贝尔佐纳(Belzona®)9611密封泄露部位；将已混合的材料挤入裂缝和孔洞中，并施加压力直到材料固化；

该操作最好使用经销商提供的贝尔佐纳(Belzona®)密封衬带完成；松开尼龙搭扣刺贴，并打开橡胶带；将橡胶带的向内卷曲端压向贝尔佐纳(Belzona®)9611，拉开紧绕维修部位的密封衬带，确保每次卷绕与先前卷绕重叠大约一半；使用尼龙搭扣刺贴作固定；

大约一小时后，拆除密封衬带并敷涂贝尔佐纳(Belzona®)1111、1121或

1221 固定修复部位；

### 4. 清洁处理

使用过的混合工具应立即使用贝尔佐纳(Belzona®)9111或任何其它有效溶剂，例如甲基乙基酮(MEK)、丙酮或纤维素稀释剂进行清洁处理。

### 5. 施工指导

a) 低压力区域施工（低于7bar/100psi/7千克/平方厘米）时，使用增强带修复即可达到满意效果；

b) 高压力区域施工时，为了确保安全性，修复时应该使用与基底材质相似的金属加固贴板；

加固贴板应该按基底轮廓塑形，并应延长出受损区域至少2.5厘米（1英寸）；

更多详情，请致电或传真贝尔佐纳(Belzona®)技术服务顾问。

### 健康安全资料

请参阅并确保了解相关的材料安全数据表

The technical data contained herein is based on the results of long term tests carried out in our laboratories and to the best of our knowledge is true and accurate on the date of publication. It is however subject to change without prior notice and the user should contact Belzona to verify the technical data is correct before specifying or ordering. No guarantee of accuracy is given or implied. We assume no responsibility for rates of coverage, performance or injury resulting from use. Liability, if any, is limited to the replacement of products. No other warranty or guarantee of any kind is made by Belzona, express or implied, whether statutory, by operation of law or otherwise, including merchantability or fitness for a particular purpose.

Nothing in the foregoing statement shall exclude or limit any liability of Belzona to the extent such liability cannot by law be excluded or limited.

Copyright © 2019 Belzona International Limited. Belzona® is a registered trademark.

贝尔佐纳产品依据 ISO 9001  
质量管理体系认证进行生产  
制造